

ET75

Property	Test Method	Unit	Value	
			MD	CD
Nominal Tensile Strength	ASTM D4595	kN/m	70	105
Elongation at Nominal Strength	ASTM D4595	%	18	18
Static Puncture Resistance (CBR)	ASTM D6241	N	9000	
Flow Rate (50mm)	ASTM D4491	l/min/m ²	1800	
Apparent Opening Size (O ₉₅)	ASTM D4751	mm	0.425	
Factory Seam Strength	ASTM D4884	kN/m	70	
UV Resistance Retained Strength (500 hrs)	ASTM D4355	%	90	

Dimension	Unit	Value
Circumference	m	4.3 / 8.6 / 12.9 / 17.2 / 21.6 / 25.9 / 30.2